

TESTERGEBNISSE

Material	Klebstoffe	Schälwerte (N/mm)
SBS	LB	8,7
	WB	9,1
SBS light	LB	7,2
	WB	9,9
SBR	LB	6,9
	WB	9,3
TPU	LB	6,9
	WB	9,3
LATEX	LB	12
	WB	14
PVC	LB	13
	WB	10
NBR	LB	11
	WB	7,5
EPDM	LB	12
	WB	11
NYLON/ PEBAX	LB	10
	WB	7,9
NYLONGEWEBE/ POLYESTERGEWEBE	LB	10
	WB	7,9
EVA/PYLON	LB	4,4
	WB	4,1
ENGAGE	LB	8,2
	WB	8,7

LB = Lösemittelbasis+ 5% UNI-DUR E 2002 ARFE

WB = Wässrige Basis

WB-Klebstoff = UNI-DUR WB 7101/EM 9 + 5% UNI-DUR WB 7075